

LOTADER[®] 9307YT

LOTADER[®] 9307YT is a random ethylene-vinyl acetate-maleic anhydride terpolymer (EVA-MAH).

- As an ethylene copolymer, LOTADER[®] 9307YT is compatible with PE in all proportions, and with most ethylene copolymers.
- Vinyl acetate brings softness, flexibility, and polarity while maleic anhydride brings reactivity, leading to versatile adhesive properties to polar and non-polar substrates.
- As a result of high-pressure polymerization in tubular reactor, LOTADER[®] 9307YT also exhibits high transparency (low haze).

LOTADER[®] 9307YT is suitable to produce thermo-adhesive films for solid substrates like PA, PET & PU films, aluminum foils, fiber mats, foams... OREVAC[®] T 9307 Y can also be used as a skin packaging adhesive on all type of cardboard.

Typical Properties

	Test Method	Unit	Typical value
Vinyl Acetate content	FTIR (Internal Method)	% wt.	14
Maleic Anhydride content	FTIR (internal method)	ppm	1600
Melt Index (190°C / 2.16 kg)	ISO 1133 / ASTM D1238	g/10min	10.5
Melting point	ISO 11357-3	°C	93
Density	ISO 1183 / ASTM D1505	g/cm ³	0.94
Vicat softening temperature (10N) ⁽¹⁾	ISO 306 / ASTM D1525	°C	66
Ring & Ball temperature	ASTM E28	MPa	145
Elongation at break ⁽¹⁾	ISO 527-2 / ASTM D638	%	800
Tensile strength at break ⁽¹⁾	ISO 527-2 / ASTM D638	MPa	19
Hardness Shore A ⁽¹⁾	ISO 868 / ASTM D2240		91

¹: On compression molded samples.

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.

Processing

LOTADER® 9307YT can be processed on most conventional equipment used for thermoplastics. It is recommended to avoid overheating above 230°C and to purge the equipment after a run is completed.

Storage, Handling & Safety

LOTADER® 9307YT should be stored in dry conditions protected from UV-light. Improper storage conditions may cause degradation and have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of LOTADER® 9307YT are available upon request to your SK Functional Polymer representative.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.