

EVATANE® 28-420

EVATANE® 28-420 is a random ethylene-vinyl acetate copolymer.

- The high Vinyl Acetate content of EVATANE® 28-420 brings softness, flexibility and polarity. EVATANE® 28-420 is compatible with most tackifying resins and waxes.
- Combined with a high fluidity, it is an efficient and easy handling product for hot melt adhesives formulations.

Typical Properties

	Test Method	Unit	Typical Value
Melt Index (190°C/2.16kg) ¹	ISO 1133	g/10min.	420
Vinyl Acetate Content	FTIR (internal method)	%wt.	28
Melting Point	ISO 11357	°C	66
Density	ISO 1183	g/cm ³	0.95
Vicat Softening Temperature (10N) ²	ISO 306	°C	<40
Tensile Strength at Break ²	ISO 527 / ASTM D638	MPa	5
Elongation at Break ²	ISO 527 / ASTM D638	%	600
Hardness Shore A ²	ISO 868 / ASTM D2240		70
Ring & Ball Temperature	ASTM E28 / NF EN 1238	°C	84

¹: Extrapolated value, measured at 125 °C / 325 g

²: On compression molded samples.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof and cannot be used as product specifications. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, SKFP expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

Processing

EVATANE® 28-420 can be processed on most conventional equipment used for thermoplastics. It is recommended to avoid melt temperatures above 230°C and to purge the equipment after a run is completed.

Storage, Handling & Safety

EVATANE® 28-420 should be stored in a ventilated area, away from heat, humidity and direct sunlight. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of the EVATANE® 28-420 are available upon request to your SK Functional Polymer representative.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.