

LOTADER[®] 18603T

LOTADER[®] 18603T is a random ethylene – methyl acrylate - maleic anhydride terpolymer.

- LOTADER[®] 18603T has been designed to coextrusion application with polyethylene, ethylene copolymers, polyamides, EVOH, PET and PS.
- LOTADER[®] 18603T can also be used as a coupling agents for HFFR compounds as well as impact modifiers for polyamides.
- LOTADER[®] 18603T is compatible with most tackifying resins and waxes and can be used in hot melt adhesives formulations. LOTADER[®] 18603T is also suitable to produce thermo-adhesive films for solid substrates like PA, PET & PU films, aluminum, foils...

Typical Properties

	Test Method	Unit	Typical value
Melt Index (190°C / 2.16 kg)	ISO 1133	g/10min	3.0
Melting point	ISO 11357	°C	92
Density	ISO 1183 / ASTM D792	g/cm ³	0.95
Vicat softening temperature (10N) ¹	ISO 306	°C	<40

¹: On compression molded samples.

Processing

LOTADER® 18603T can be processed with standard polyolefin equipment over a wide range of temperature, up to 300°C. For instance, when extruded through sheet coextrusion, temperature settings could be:

Zone 1	Zone 2	Zone 3	Zone 4	Fittings-Channels	Die
150-170°C	170°C	170°C	170°C	170°C	170°C

Storage, Handling & Safety

LOTADER® 18603T should be stored in a ventilated area, away from heat, humidity and direct sunlight. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Due to its physical properties (Vicat temperature <40°C), it may be possible that the product shows some caking. This is particularly true during summertime.

Safety data sheet as well as information on handling and storage of LOTADER® 18603T are available upon request to your SK Functional Polymer representative or at www.sk-fp.com.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof and cannot be used as product specifications. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, SKFP expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.