

LOTADER[®] AX8850

LOTADER[®] AX8850 is a random ethylene - glycidyl methacrylate copolymer (E-GMA).

- The glycidyl methacrylate group gives reactivity with chemical functions such as OH, COOH and NH₂ groups leading to its optimal dispersion during melt mixing with engineering thermoplastics (PET, PBT, PPS...).
- LOTADER[®] AX8850 high fluidity combined with the high GMA content yields to compounds targeting injection molding.
- LOTADER[®] AX8850 is a good compatibilizer of PET/PE, PBT/PE blends and is therefore recommended for the mechanical recycling of these blends.
- As an ethylene copolymer, LOTADER[®] AX8850 is compatible with LDPE and with many ethylene copolymers.
- LOTADER[®] AX8850 is also a good adhesion promoter when blended with polyolefin.

Typical Properties

	Test Method	Unit	Typical Value
Melt Index (190°C/2.16kg)	ISO 1133	g/10min	40
Glycidyl Methacrylate Content	FTIR (internal method)	%wt	12
Melting Point	ISO 11357	°C	98
Density	ISO 1183 / ASTM D792	g/cm ³	0.94
Vicat Softening Temperature (10N) ¹	ISO 306	°C	64
Tensile Strength at Break ¹	ISO 527 / ASTM D638	MPa	7.9
Elongation at Break ¹	ISO 527 / ASTM D638	%	600
Tensile modulus ¹	ISO 527 / ASTM D638	MPa	80
Flexural Modulus ¹	ISO 178	MPa	77
Hardness Shore A/D(15s) ¹	ISO 868 / ASTM D2240	-	93 / 38

¹: On compression molded samples.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof and cannot be used as product specifications. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, SKFP expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

Processing

Heat stability of acrylate comonomer allows processing temperatures as high as for polyesters (PBT, PET) and PPS, which are the main material using LOTADER® AX8850 as impact modifier.

CAUTION: LOTADER® AX8850 reacts with polymers containing maleic anhydride and acid functions. This reaction may generate gels or can block an extruder if not controlled. Extruders must be thoroughly purged before and after extruding LOTADER® AX8850.

Storage, Handling & Safety

LOTADER® AX8850 should be stored in a ventilated area, away from heat, humidity and direct sunlight. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of the LOTADER® AX8850 are available upon request to your SK Functional Polymer representative or at www.sk-fp.com.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.