

LOTADER[®] AX8900

LOTADER[®] AX8900 is a random ethylene-methyl acrylate-glycidyl methacrylate terpolymer (E-MA-GMA).

- Acrylic ester brings softness and polarity, while keeping high thermal stability during processing.
- The high content of acrylic ester leads to high flexibility (low crystallinity) and high impact absorption behaviour.
- Glycidyl methacrylate gives reactivity (versus OH, COOH and NH₂ groups), leading to optimal dispersion during melt mixing with engineering thermoplastics.
- As an ethylene copolymer, LOTADER[®] AX8900 is compatible with LDPE in all proportions, and with almost all other ethylene copolymers.

LOTADER[®] AX8900 is suitable as:

- additive to improve impact strength of engineering thermoplastics (PPS, PBT, PET) and PC/PBT, PC/PET and PC/ABS alloys,
- compatibilizer for polyesters/polyolefins blends and in some formulated adhesive tapes,
- bitumen performance enhancer / additive for asphalt modification,
- adhesion promoter onto metallic surface.

Typical Properties

	Test Method	Unit	Typical Value
Melt Index (190°C/2.16kg)	ISO 1133	g/10min.	6
Methyl Acrylate Content	FTIR (internal method)	%wt.	24
Glycidyl Methacrylate Content	FTIR (internal method)	%wt.	8
Melting Point	ISO 11357	°C	75
Density	ISO 1183 / ASTM D792	g/cm ³	0.95
Vicat Softening Temperature (10N) ¹	ISO 306	°C	<40
Tensile Strength at Break ¹	ISO 527 / ASTM D638	MPa	4
Elongation at Break ¹	ISO 527 / ASTM D638	%	1100
Flexural Modulus ¹	ISO 178 / D790	MPa	<30

¹: On compression molded samples.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof and cannot be used as product specifications. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, SKFP expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

Processing

Heat stability of acrylate comonomer allows processing temperatures as high as for polyesters (PBT, PET) and PPS, which are the main material using LOTADER® AX8900 as impact modifier.

CAUTION: LOTADER® AX8900 reacts with polymers containing maleic anhydride and acid. This reaction may generate gels or can block an extruder if not controlled. Extruders must be thoroughly purged before and after extruding LOTADER® AX8900.

Storage, Handling & Safety

LOTADER® AX8900 should be stored in a ventilated area, away from heat, humidity and direct sunlight. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Due to its physical properties (Vicat temperature <40°C), it may be possible that the LOTADER® AX8900 shows some caking. This is particularly true during summertime.

Safety data sheet as well as information on handling and storage of the LOTADER® AX8900 are available upon request to your SK Functional Polymer representative or at www.sk-fp.com.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.