

LOTRYL[®] BESTPEEL 2407

LOTRYL[®] BESTPEEL 2407 is a ready-to-use thermoplastic composition designed to make peelable heat seal layers onto various substrates. The base resin is a random ethylene-methyl acrylate copolymer.

- Used as top layer of laminates in order to provide the functions of heat sealability onto various substrates like PP, PS, PET and PVC, and easy opening by interfacial peeling.
- Easily processed using the technologies of coextrusion coating, cast film coextrusion, blown film coextrusion or sheet coextrusion, to produce multilayers that can be used as lids, directly or after lamination with other films.

Typical Properties

	Test Method	Unit	Typical Value
Methyl Acrylate Content	FTIR (internal method)	%wt.	23
Melt Index (190°C/2.16kg)	ISO 1133	g/10min.	2
Melting Point	ISO 11357	°C	69
Density	ISO 1183		0.94
Vicat Softening Temperature (10N) ¹	ISO 306	°C	<40
Flexural Modulus ¹	ISO 178	MPa	14
Elongation at Break ¹	ISO 527 / ASTM D638	%	800
Hardness Shore A ¹	ISO 868 / ASTM D2240		79

¹: On compression molded samples.

Processing

LOTRYL®BESTPEEL 2407 can be used as peelable heat seal layer in many kinds of lid constructions, based on aluminum foil, plastic films, paper, or a combination of them.

Structure examples:

Reverse printed bi-oriented film / adhesive / LDPE / LOTRYL®BESTPEEL 2407

Aluminum / adhesive / LDPE / LOTRYL®BESTPEEL 2407

Such constructions are heat sealable onto PP, PS, APET and PVC. Sealing strength is dependent on factors related to the different materials involved (heat conductivity, thicknesses) and to technological parameters like shape of the sealing tools, actual pressure, and time.

As general recommendations, flat sealing bars and moderate pressure should be preferred for better results and less squeezing of the sealing layer. Sealing temperature should be in the range from 160-180°C to 220-240°C, depending on heat conductivity of the whole structure and on contact time.

Storage, Handling & Safety

LOTRYL®BESTPEEL 2407 should be stored in a ventilated area, away from heat, humidity and direct sunlight. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of the LOTRYL®BESTPEEL 2407 are available upon request to your SK Functional Polymer representative or at www.sk-fp.com.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.