

# OREVAC® 18341

OREVAC® 18341 is a maleic anhydride (MAH) grafted linear low-density polyethylene.

- OREVAC® 18341 has been designed to develop a reliable bonding strength between polyethylene or ethylene copolymers and mineral fillers such as aluminum trihydrate (ATH) or magnesium hydroxide (MDH). It is an effective coupling agent for halogen-free flame retardant compounds using high loadings of mineral fillers, such as compounds for insulation and sheathing of wires and cables.
- OREVAC® 18341 can also be used as a tie layer in pipe-coating technology for multi-layer structures. It has been designed to develop a reliable bonding strength onto FBE (Fusion Bonded Epoxy) steel pipe protective layer
- In packaging market, OREVAC® 18341 develops a reliable bonding strength in coextrusion processes between polyethylene and different materials (PA, EVOH ...). Containing a higher amount of grafted reactive functionalities compared to standard LLDPE based coextrusion tie resins, it can be used blended with other polyolefins.

## Typical Properties

	Test Method	Unit	Typical Value
Melt Index (190°C/2.16kg)	ISO 1133	g/10min.	1.5
Melting Point	ISO 11357	°C	121
Grafted MAH content	Internal	%	> 1
Density	ISO 1183 / ASTM D792	g/cm <sup>3</sup>	0.92
Vicat Softening Temperature (10N) <sup>1</sup>	ISO 306	°C	95
Tensile modulus <sup>1</sup>	ISO 527 / ASTM D638	MPa	250
Elongation at break <sup>1</sup>	ISO 527 / ASTM D638	%	>600
Tensile strength at break <sup>1</sup>	ISO 527 / ASTM D638	MPa	>20
Hardness Shore D (1s/15s) <sup>1</sup>	ISO 868 / ASTM D2240		55/45

<sup>1</sup>: On compression molded samples.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof and cannot be used as product specifications. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, SKFP expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

## Processing

OREVAC® 18341 is suitable for the production of cable compounds with most common types of equipment (internal mixer, co-kneader, twin screw extruder). When used for pipe coating technology, OREVAC® 18341 is to be processed like a standard polyethylene resin. Typical extrusion temperature settings could be:

Zone 1	Zone 2	Zone 3	Zone 4	Exit	Fittings-Channels	Die
180-190°C	190-200°C	200-210°C	210-220°C	220-230°C	220-240°C	220-240°C

Final profile and settings will depend on the line and the multi-layer structure being run.

## Storage, Handling & Safety

OREVAC® 18341 should be stored in a ventilated area, away from heat, humidity and direct sunlight. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of the OREVAC® 18341 are available upon request to your SK Functional Polymer representative or at [www.sk-fp.com](http://www.sk-fp.com).

## Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.