

OREVAC[®] 18751

OREVAC[®] 18751 is a maleic anhydride grafted polypropylene.

- OREVAC[®] 18751 is a tie resin to be used in extrusion coating and extrusion lamination technologies. It has been designed to develop adhesion in these processes onto substrates like aluminium foil, paper or PP films and in coextrusion with resins like PP and PA.
- OREVAC[®] 18751 exhibits excellent processing properties, particularly regarding drawability, neck-in and melt stability. In addition to adhesive properties, OREVAC[®] 18751 allows to design aluminium lids for PP or PP coated cups and containers with controlled opening forces.

Typical Properties

	Test Method	Unit	Typical Value
Melt Index (230°C/2.16kg)	ISO 1133	g/10min.	35
Grafted MAH content	Internal	%	< 0.2
Melting Point	ISO 11357	°C	160
Density	ISO 1183 / ASTM D792	g/cm ³	0.91
Vicat Softening Temperature (10N) ¹	ISO 306	°C	138
Tensile modulus ¹	ISO 527 / ASTM D638	MPa	650
Tensile strength at yield ¹	ISO 527 / ASTM D638	MPa	22
Elongation at break ¹	ISO 527 / ASTM D638	%	500

¹: On 25 µm films

Processing

OREVAC® 18751 is not corrosive and is readily processed with standard polyolefin equipment. Conditions typically used in extrusion of polypropylene resins are suitable. Typical extrusion temperature settings could be:

Zone 1	Zone 2	Zone 3	Zone 4	Fittings-Channels	Die
200-220°C	220-250°C	250-275°C	275°C	275°C	275°C

Final profile and settings will depend on the line and the multi-layer structure being run. Although it is not necessary for short runs, it is recommended to dry OREVAC® 18751 pellets prior to extrusion in order to reduce die build-up during long runs. Typical drying conditions would be from 2 to 4 hours at 80-90°C under dry air.

Storage, Handling & Safety

OREVAC® 18751 should be stored in a ventilated area, away from heat, humidity and direct sunlight. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of the OREVAC® 18751 are available upon request to your SK Functional Polymer representative or at www.sk-fp.com.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof and cannot be used as product specifications. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, SKFP expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN.

The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.